


FS-H62710 ULTRA Glacier 250

Microporous Resin-Coated Paper

Printability

- simplex printable



Product Specification

Property	Test Method	Dimension	Target	Tolerance
Weight	DIN EN ISO 536	g/m ²	243	± 7
Thickness	DIN EN ISO 534	µm	243	± 6
	DIN EN ISO 536	mil	9.6	± 0.23
Gloss BYK	ISO 2813	60°	18	± 5
Colour Elrepho UVO (D65)	ISO 2469	L	94,5	± 0,8
		a	-0,2	± 0,5
		b	-1,8	± 0,8
		delta b	9,9	± 0,8
CIE Whiteness (D65/10°) min.	ISO 2469		> 139	
Opacity min.	ISO 2469	%	> 90	

Printing Technology

- Inkjet water-based

Key Applications

- Photos
- Photo cards
- Photo cards
- Photo Retail
- Poster / Wall Decoration

Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

www.dicavesa.com



FS- H62710 ULTRA Glacier 250

Microporous Resin-Coated Paper

Benefits & Properties

- Pin-sharp details
- High colour consistency and gamut
- Vivid colours
- High colour consistency
- Water resistance
- High opacity
- High light fastness
- Outstanding lay-flat performance

Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

www.dicavesa.com



Photo Classic
INKJET MEDIA