

POLI-LUX 700 GLOSS

TECHNICAL DATA

Carrier material: Monomeric PVC film, highly stabilized, calendered

Thickness: 80 µm (ISO 4593)

Adhesive: Ultra-Clear Acrylic Dispersion, permanent

Adhesion: 6,5 N/cm (Finat FTM 1, n. 24 hrs on stainless steel)

Dimensional stability: Shrinkage < 0.4 mm (Finat FTM 14)

Liner: One-sided clay-coated Silicone paper (90 g/m²)

Tensile strength md: > 20 MPa (DIN EN ISO 527)

Tensile strength cd: > 20 MPa (DIN EN ISO 527)

Elongation md: > 160 % (DIN EN ISO 527)

Elongation cd: > 180 % (DIN EN ISO 527)

Application temperature: > +10° C

Temperature resistance: - 40° C - +80° C

Outdoor resistance: 3 years (unprinted material, vertical outdoor exposure, central European normal climate)

SAFETY DATA SHEET

When used under normal conditions, this product does not generate or release any dangerous substances or hazardous chemicals. This is a non-hazardous product in accordance with the current GefStoff V and EU criteria. Therefore it is not necessary to prepare a Material Safety Data Sheet for this product. The Safety Data Sheet serves only to comply with the regulation to supply information in accordance with REACH Regulation (EC) No. 1907/2006 (REACH) and is available on request. This product is not a hazardous product with regards to transportation legislation; neither does it contain substances that are hazardous to water within the meaning of the federal water act. After use, dispose of the waste product in accordance with the local / national authorities.

PRODUCT DETAILS

- POLI-LUX 700 Gloss is a Monomeric PVC-Film (transparent gloss, 80 µm)
- Laminated with a one-sided clay-coated silicone paper (90 g/m²) and equipped with an ultra-clear dispersion acrylic adhesive (permanent)
- Suitable for bonding various surfaces for example on commercial slabs, glass, metal or plastic
- Especially suitable for the use on smooth as well as slightly curved surfaces
- POLI-LUX 700 Gloss is ideal for short to mid-term presentation of advertising panels

PRODUCT BENEFITS

- Very good transparency and flatness characteristics
- Excellent dimensional stability and enhanced image brightness
- High quality laminating film suitable to protect digital prints and images against the influence of UV, dirt and humidity
- Fire classification B1 Certification and in accordance to DIN 4102-1 flame resistant adhered on steel surface
- POLI-LUX 700 Gloss improves the outdoor resistance of the print and reduces fading and damage caused from outdoor exposure

**PROCESSING
INSTRUCTIONS &
PRINTING**

- The print must be completely dry before laminating, a minimum of 48 hours drying time is recommended
- The surface which is to be laminated should be free from any impurities to achieve optimal adhesion to the digital printed film
- Detailed printing settings and numerous ICC-Profiles can be found on our homepage www.poli-tape.de
- Additional suggestions and processing details can be downloaded from our homepage

**TRANSPORT AND
STORAGE**

- 2 years if stored in original packaging at ca. 22° C and 50 - 55% relative humidity
 - Printed material should be completely dry and protected during transportation
 - Temperature and humidity fluctuations should be avoided
-

DISCLAIMER

The information on the physical and chemical properties and values contained in this document is based on tests we believe to be reliable; however, it does not constitute a guarantee. It is provided for informational purposes only, without warranty, and does not establish any guarantee. Buyers should independently verify the suitability of this material for their specific intended use prior to use. All technical data is subject to change. All POLI-TAPE products are sold in accordance with the terms and conditions of sale. For further information, please contact your POLI-TAPE sales representative. In the event of any ambiguity or discrepancy between the English version and foreign-language versions of this document, the English version shall prevail and take precedence.

POLI-TAPE Klebefolien GmbH
Zeppelinstraße 17
53424 Remagen - GERMANY
Phone: +49 2642 - 98 36 0
Fax: +49 2642 - 98 36 37
Email: info@poli-tape.de
Internet: www.poli-tape.de